(BSP August 4, 2003)

Prestressed Concrete Girders

Aggregates and Proportioning

The second paragraph of Section 9-19.1 is revised to read as follows:

The Contractor shall submit a Contractor-Provided mix design for each design strength of prestressed girder to the Engineer for approval in accordance with Section 6-02.3(2)A, including a Contractor-Provided mix design of high strength concrete for the prestressed girders of *** $$1$$ ***.

Approval of the mix design will not preclude any requirements for the concrete placed in the girders.

The Contractor-Provided mix design for high strength concrete shall conform to the following:

Bridge	Minimum Compressive Strength in kPa at 56 days in accordance with AASHTO T 22
*** $$2$$ ***	*** $$3$$ ***

The Contractor may substitute testing for minimum compressive strength at 28 days, provided that the 28 day compressive strength is equal to or greater than 95 percent of the specified 56 day compressive strength.

The Contractor shall test a minimum of three specimens for each of the tests specified. The test specimens for the compressive strength tests shall be 100 millimeter by 200 millimeter cylinders cast in molds supplied by the Contractor in accordance with Section 6-02.3(5)D. The Contractor shall include the results of all tests in the high strength concrete mix design submittal to the Engineer.